T 28. 14: 989-90

WORLD COINAGE REPORT

1989 1990

United States Mint
Department of the Treasury
United States of America

ISBN 0-16-036231-8

For sale by the U.S. Government Printing Office
Superintendent of Documents, Mail Stop: SSOP, Washington, DC 20402-9328
ISBN 0-16-036231-8

U. S. GPO
Depository 336

JUL 1 4 1993

Washington University Libraries
St. Louis, MO 63130

World Coinage Report

1989-1990

United States Mint
Department of the Treasury

For sale by the Superintendent of Documents, U.S. Government Printing Office
Washington, D.C. 20402

ACKNOWLEDGEMENT OF SOURCE DATA

The United States Mint sincerely thanks the many foreign governments that responded to its interrogatories. These interrogatories were the sole source of data for this report.

Special thanks also go to those governments that supplied photographs, sketches, or samples of their coins. Unfortunately, for technical reasons, many of the submissions could not be reproduced in a way that would fairly represent the aesthetic details of the coins. Thus, we are forced to omit the illustrations altogether. Nonetheless, the Mint is grateful for the submissions.

Finally, the Mint extends its appreciation to the Department of State, Washington, D.C., and its personnel overseas for receiving and transmitting the data.



Eugene H. Essner
Deputy Director of the Mint

Explanatory notes on tables

Do or *do* are abbreviations for ditto, meaning that the information is the same as that appearing immediately above. Numbers in the tables are expressed in figures arranged to conform to usage in the United States, that is, in groups of three figures separated by a comma (,). For example, one thousand is written 1,000 and one million is written 1,000,000. Fractional or decimal parts of a whole number are set off by a period (.). For example, one tenth is written 0.1, one hundredth 0.01, one thousandth 0.001, and so on.

Pieces. — The figures in this column indicate the number of pieces reported as actually manufactured by a coinage mint or mints during the calendar year indicated. Leaders (dots....) in this column indicate that no coins of that particular type were reported to have been manufactured.

Specifications of coins. — Specifications are for a single coin of the stated denomination and, in general, represent standards provided by law, decree, or regulation of the issuing government. However, details concerning tolerances of weight and fineness, and other minting controls and procedures are not published. For uniformity, different units of weight are converted to grams and different units of measure are converted to millimeters. The following conversion factors were used:

Weight units	Measurement units
1 gram = 15.43235639 grains.	1 inch = 25.4 millimeters.
1 grain = 0.0647989182 gram.	1 millimeter = 0.03937 inch.

Gross weight. — This refers to the overall weight of one coin of the specified denomination.

Metallic composition. — The proportions of metals are expressed either in percentages (symbol %) with the proportions adding to 100 percent; or, for gold and silver coins, in thousands with the proportions of precious metal and base metal adding to 1,000 parts.

Thickness. — Thicknesses of coins usually are not prescribed by government decree or law as in the case of diameters. Thicknesses cannot be so specified since they vary according to minting practices and other factors relating to coins. Thicknesses in the tables are to be regarded as averages which may vary slightly over or under the figures shown.

Shape of coins. — Coins are round unless otherwise indicated.

Coinage metal symbols:

Al - Aluminum
Ag - Silver
Au - Gold
Cr - Chromium
Cu - Copper
Mg - Magnesium
Mn - Manganese
Ni - Nickel
Sn - Tin
Zn - Zinc

ALGERIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
10 dinars	92% CU, 6% Al, 2% Ni	11.25	29.50	2.36	Milled	1,582,400	.....
5 dinars	100% Ni	12.00	31.00	2.22	.....do.....	6,623,000	7,745,600
1 dinar	75% Cu, 25% Ni	7.00	25.00	1.97	.....do.....	8,535,750	34,583,500
50 centimes	79% Cu, 20% Zn, 1% Ni	5.00	24.00	1.50	.....do.....	4,898,500	19,543,803
20 centimes	.....do.....	4.00	22.00	1.50	Plain	5,485,500	.....
10 centimes	95% Al, 5% Mg	1.65	24.00	1.75	.....do.....	1,839,000	3,557,000
5 centimes	.....do.....	1.50	22.00	1.90	.....do.....	2,584,000	3,175,000
Total						31,548,150	68,604,903

NOTE: Coins produced by the Banque d'Algerie.

AUSTRALIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
2 dollars	92% Cu, 6% Al, 2% Ni	6.60	20.62	3.00	Milled	29,300,000	9,664,500
10 cents	75% Cu, 25% Ni	5.65	23.72	1.98	Reeded	73,125,000	17,603,000
5 cents	do	2.83	19.53	1.55	do		36,970,000
2 cents	97% Cu, 2.5% Zn, 0.5% Sn	5.20	21.72	2.03	Smooth	89,114,000	35,385,000
1 cent	do	2.60	17.65	1.58	do	156,114,000	70,035,500
Numismatic:[1]							
200 dollars	917 Au, 83 Ag and Cu	10.00	24.20	2.00	Reeded	55,565	22,344
10 dollars	925 Ag, 75 Cu	20.00	34.10	2.90	do	92,329	128,046
5 dollars	92% Cu, 6% Al, 2% Ni	28.00	38.74	3.45	do	22,535	1,043,001
2 dollars	925 Ag, 75 Cu	6.60	20.62	3.00	Milled	80,594	
Do	92% Cu, 6% Al, 2% Ni	6.60	20.62	3.00	do	218,937	187,691
1 dollar	do	9.00	25.12	2.80	do	245,971	189,929
50 cents	75% Cu, 25% Ni	15.55	31.65	2.80	Smooth	231,991	180,728
20 cents	do	11.30	28.52	2.41	Reeded	244,903	162,561
10 cents	do	5.65	23.60	1.90	do	253,396	162,561
5 cents	do	2.83	19.41	1.45	do	260,932	162,561
2 cents	97% Cu, 2.5% Zn, 0.5% Sn	5.20	21.59	1.98	Smooth	240,340	162,561
1 cent	do	2.60	17.53	1.55	do	358,019	162,561
Total						349,958,512	172,222,544

[1] Numismatic figures include 162,011 uncirculated 8 coin sets, 94,068 uncirculated 10 dollar, 23,265 uncirculated 200 dollar (gold) coins, 50,303 proof 10 dollar (silver) coins, 72,811 proof 8 coin sets.22,535 proof 5 dollar and 28,236 proof 200 dollar (gold) coins for 1989 and 118,326 uncirculated 8 coin sets, 1,000,000 uncirculated 5 dollar, 25,130 uncirculated 10 dollar (silver), 3,817 uncirculated 1 dollar, 8,540 uncirculated 200 dollar (gold) coins, and 57,215 proof 8 coin sets, 2,500 proof 1 dollar, 21,051 proof 1 dollar (silver), 50,000 proof 5 dollar and 13,804 proof 200 (gold) coins for 1990.

NOTE: Coinage produced by the Royal Australian Mint. All coins dated year of mintage.

AUSTRIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
2000 schilling	9999 Au	31.10	37.00	2.00	Reeded	430,500	401,000
500 schilling	.....do	7.80	22.00	1.20	.....do.....	436,000	46,000
Do	925 Ag. 75 Cu	24.00	37.00	2.50	Lettered	622,800	677,500
20 schilling	92% Cu. 6% Al. 2% Ni	8.00	27.70	1.90	19 Points	280,000	750,000
10 schilling	75% Cu. 25% Ni	6.20	26.00	1.60	Reeded	16,261,000	27,190,000
5 schilling	.....do	4.80	23.50	1.40	Plain	24,071,000	36,552,000
1 schilling	91.5% Cu. 8.5% Ni	4.20	22.50	1.55	.....do.....	62,849,000	103,750,000
50 groschen	.....do	3.00	19.50	1.50	Reeded	17,381,000	29,693,000
10 groschen	98.5% Al. 1.5% Mg	1.10	20.00	1.40	Plain	127,812,000	182,090,000
5 groschen	99% Zn	2.50	19.00	1.50	Reeded	2,632,000	2,648,000
2 groschen	98.5% Al. 1.5% Mg	0.90	18.00	1.50	Plain	978,000	40,000
Total						253,753,300	383,837,500

NOTE: All coinage produced by the Austrian Mint. All coins dated year of mintage.

BAHAMAS

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
2500 dollars	916.7 Au	407.27	72.00	n.a.	Reeded	32	.....
250 dollars	916.7 Au	47.54	38.61	n.a.	.....do.....	53	110
100 dollars	900 Au	6.48	22.00	n.a.	.....do.....	854	135
25 dollars	925 Ag	136.08	63.00	n.a.	.....do.....	954	421
10 dollars	.....do	28.28	38.61	n.a.	.....do.....	1,704	596
5 dollars	.....do	19.44	36.00	n.a.	.....do.....	4,000	4,000
2 dollars	.....do	16.85	34.00	n.a.	.....do.....	4,000	4,000
1 dollar	Cupro-Nickel	18.14	32.00	n.a.	.....do.....	12,000	2,000
50 cents	.....do	10.37	29.01	n.a.	.....do.....	12,000	2,000
25 cents	Nickel	6.80	24.26	n.a.	.....do.....	12,000	2,000
15 cents	.....do	6.48	21.59	n.a.	.....do.....	12,000	2,000
10 cents	.....do	5.51	23.50	n.a.	.....do.....	12,000	2,000
Do	75% Cu. 25% Ni	5.51	23.50	1.80	Smooth	5,000,000	.....
5 cents	Cupro-Nickel	3.89	21.01	n.a.	Reeded	12,000	2,000
1 cent	97.5% Zn. 2.5% Cu	2.50	19.05	1.58	Smooth	.....	20,000,000
Do	Cupro-Zinc	2.50	19.05	n.a.	Reeded	12,000	2,000
Total						5,095,597	20,023,262

NOTE: Coinage variously produced by the Royal Mint, U.K. and the Stuttgart Mint, Germany. All coins dated 1989 except 2500 dollars, which are dated 1988.
n.a - Not available.

BANGLADESH

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*

NOTE: No coins were produced in 1989 and 1990.

BARBADOS

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
1 dollar	75% Cu, 25% Ni	6.25	26.00	2.00	Plain	3,336,000	.....
25 cents	do	5.65	23.60	1.50	Milled	.....	2,500,000
10 cents	do	2.26	17.78	1.00	do	2,520,000	2,500,000
5 cents	80% Cu, 20% Zn	3.75	21.00	1.50	Plain	2,533,000	.....
1 cent	97.5% Zn, 2.5% Cu	2.50	19.00	1.50	do	12,000,000	15,000,000
Total						20,389,000	20,000,000

NOTE: All coins produced by the Royal Canadian Mint. All coins dated year of mintage.

BELGIUM

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989[1]	1990[2]
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
500 francs	Ag 833. Cu 167	22.85	37.00	2.60	Plain	.....	730,000
50 francs	99% Ni	7.00	22.75	2.30	Reeded	35,948,000	31,052,000
1 franc	94% Fe. 6% Ni	2.75	18.00	1.75	.....do.....	290,220,000	321,350,000
Bullion coins:							
100 ecu	Au 999	31.10	37.00	n.a.	Plain	102,000	5,000
Do	.....do.....	62.20	37.00	n.a.	.....do.....	1,000	.....
50 ecu	.....do.....	15.55	29.00	n.a.	.....do.....	102,000	5,000
25 ecu	.....do.....	7.78	21.00	n.a.	.....do.....	102,000	5,000
20 ecu	Bimetal Au 900. Ag 833	10.50	29.00	n.a.	.....do.....	.....	33,560
10 ecu	Au 999	3.11	16.00	n.a.	.....do.....	2,000	5,000
Do	Bimetal Au 900. Ag 833	5.30	22.00	n.a.	n.a.	.....	38,543
Total						326,477,000	353,224,103

[1] 1989 figures include 7,000,000 50 franc coins dated 1988; all others dated year of mintage.

[2] 1990 figures include 1.052,000 50 franc and 109,780.000 1 franc coins dated 1989, all others dated year of mintage.

NOTE: Coinage produced by the Royal Mint, Brussels.

n.a. - Not available.

BOLIVIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*

NOTE: No coins were produced in 1989 and 1990.

BOTSWANA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
25 thebe	Cupro Nickel	5.73	25.00	n.a.	Milled	2,000,000	.....
10 thebe	.....do	3.83	22.00	n.a.	.....do.....	4,000,000	2,080,000
5 thebe	Bronze	2.70	19.50	n.a.	.....do.....	.....	2,000,000
1 thebe	Aluminum	0.70	18.50	n.a.	.....do.....	.....	5,800,000
Total						6,000,000	9,880,000

NOTE: Coinage produced by the Royal Mint, U.K. All coins dated 1989.
n.a. - Not available.

BRAZIL

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
50 cruzeiros	Stainless Steel	4.78	23.50	1.40	Smooth	.....	10,000,000
10 cruzeiros	.....do	4.36	22.50	1.40	.....do.....	.....	413,000,000
5 cruzeiros	.....do	3.97	21.50	1.40	.....do.....	.....	517,000,000
1 cruzeiro	.....do	3.61	20.50	1.40	.....do.....	.....	377,000,000
50 centavos	.....do	2.83	19.50	1.50	.....do.....	453,800,000	216,644,000
10 centavos	.....do	2.54	18.50	1.50	.....do.....	362,900,000	136,000,000
5 centavos	.....do	2.26	17.50	1.50	.....do.....	270,400,000	934,000
1 centavo	.....do	2.01	16.50	1.50	.....do.....	208,100,000	1,000,000
Commemorative:							
200 cruzados	Silver 999	13.47	31.00	2.10	Milled	30,000	.....
1 cruzado	Stainless Steel	9.95	31.00	2.00	Smooth	10,000,000	.....
Total						1,305,230,000	1,671,578,000

NOTE: All coins dated year of mintage. Cruzado removed in 1989.

CANADA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
1 dollar	91.5% Ni Core. 8.5% Bronze Plating	7.00	26.50	1.95	11- sided	186,024,941	68,402,000
50 cents	100% Ni	8.10	27.13	1.90	Milled	.....	207,000
25 cents	.....do.....	5.05	23.88	1.58	.....do.....	119,084,307	31,312,000
10 cents	.....do.....	2.07	18.03	1.22	.....do.....	198,693,414	64,811,000
5 cents	75% Cu, 25% Ni	4.60	21.20	1.76	Plain	141,460,538	42,537,000
1 cent	98% Cu, 1.5% Zn, 0.5% Sn	2.50	19.10	1.45	12- sided	1,069,178,072	216,096,000
Bullion coins:							
50 dollars	9999 Au	31.15	30.00	2.80	Milled	856,000	815,000
Do	9995 Plt	31.16	30.00	2.52	.....do.....	10,000	15,100
20 dollars	9999 Au	15.58	25.00	2.20	.....do.....	259,200	174,400
Do	9995 Plt	15.54	25.00	2.02	.....do.....	4,800	2,600
10 dollars	9999 Au	7.80	20.00	1.70	.....do.....	328,800	253,600
Do	9995 Plt	7.80	20.00	1.50	.....do.....	3,200	1,600
5 dollars	9999 Au	3.13	16.00	1.22	.....do.....	539,000	476,000
Do	9995 Plt	3.13	16.00	1.01	.....do.....	18,000	9,000
Do	9995 Ag	31.39	32.00	3.21	.....do.....	3,332,200	1,708,800
Numismatic:							
200 dollars	916.7 Au	n.a.	n.a.	n.a.	n.a.	.....	18,040
100 dollars	583 Au	13.33	26.90	2.18	Milled	59,657	47,845
1 dollar	500 Ag, 500 Cu	23.33	36.07	2.93	.....do.....	498,529	452,960
Do	91.5% Ni Core, 8.5% Bronze Plating	15.62	32.13	2.65	11- sided	380,184	359,565
50 cents	100% Ni	8.10	27.13	1.90	Milled	380,184	359,565
20 cents	.....do.....	5.07	23.88	1.60	.....do.....	380,184	359,565
10 cents	.....do.....	2.07	18.03	1.22	.....do.....	380,184	359,565
5 cents	75% Cu, 25% Ni	4.60	21.20	1.80	Plain	380,184	359,565
1 cent	98% Cu, 1.5% Zn, 0.5% Sn	2.50	19.05	1.50	12- sided	380,184	359,565
Total						1,722,631,762	429,497,335

NOTE: Coinage produced by the Royal Canadian Mint.

CHINA, PEOPLE'S REPUBLIC OF

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
5 fen	98.1% Al. 1.5% Mg. 0.4% Mn	1.60	24.00	1.80	Milled	1,500,000,000	1,920,000,000
2 fen	do	1.08	21.00	1.60	do	3,402,150,000	1,252,700,000
Commemorative:							
1 yuan	75% Cu. 25% Ni	9.32	30.00	1.70	do	21,000,000	.....
Do	n.a	8.40	30.00	1.70	do	.....	25,608,000
Total						4,923,150,000	3,198,308,000

NOTE: Coinage produced by the China Banknote Printing and Minting Corporation, Peoples Bank of China. Coins variously dated 1984, 1986, 1987, 1988, 1989 and 1990.
n.a. - Not available

COLOMBIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
50 pesos	65% Cu. 20% Zn. 15% Ni	8.40	26.50	1.70	Lettered	30,308	.....
Do	.....do	4.49	21.50	1.40	Reeded	50,388,100	120
20 pesos	92% Cu. 6% Al. 2% Ni	6.00	24.50	1.60	Smooth	20,165	.....
Do	.....do	3.61	20.00	1.40	Reeded	69,897,600	130
10 pesos	65% Cu. 20% Zn. 15% Ni	10.00	26.00	1.85	Smooth	26,012	.....
Do	.....do	3.32	18.50	1.40	Reeded	158,194,100	91,300
5 pesos	92% Cu. 6% Al. 2% Ni	2.61	17.00	1.40	.....do.....	106,825,923	100,700
Total						385,382,208	192,250

NOTE: Coinage produced by the Colombian Mint. All coins dated year of mintage.

CYPRUS

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
20 pounds	916.7 Au, 83.3 Cu	7.99	22.05	n.a.	Milled	.....	5,000
1 pound	75% Cu, 25% Ni	28.28	38.61	n.a.	Plain	38,000	.....
Do	925 Ag, 75 Cu	28.28	38.61	n.a.	.....do.....	13,000	.....
20 cents	70% Cu, 24.5% Zn, 5.5% Ni	7.75	27.25	1.84	Milled	2,008,000	3,000,000
10 cents	.....do.....	5.50	24.50	1.72	.....do.....	.....	4,000,000
5 cents	.....do.....	3.75	22.00	1.40	Plain	.....	4,000,000
2 cents	.....do.....	2.50	19.00	1.28	.....do.....	.....	4,000,000
1 cent	.....do.....	2.00	16.50	1.35	.....do.....	.....	4,000,000
Total						2,059,000	19,005,000

NOTE: All coinage produced by the Royal Mint, U.K. except for 20 pound coins produced by the Royal Canadian Mint and the 1 pound silver coins produced by the Administration des Monnais et Medailles, Paris.

n.a. - Not available.

CZECHOSLOVAKIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
50 haleru	80% Cu, 20% Ni	3.20	20.80	1.30	Reeded	13,000,000	12,000,000
20 haleru	79% Cu, 20% Zn, 1% Ni	2.60	19.50	1.25	ditto	30,000,000	26,000,000
10 haleru	98% Al, 2% Mg	0.90	18.20	1.50	Plain	50,510,000	24,950,000
5 haler	ditto	0.75	16.20	1.60	ditto	8,000,000	6,000,000
10 korun	92% Cu, 6% Al, 2% Ni	8.00	24.50	2.45	Plain[1]	...	10,000,000
5 korun	80% Cu, 20% Ni	7.00	26.00	1.90	Patterned	5,009,000	5,000,000
2 koruny	ditto	6.00	24.00	1.80	ditto	9,062,000	15,000,000
1 korun	91% Cu, 8% Al, 1% Mn	4.00	23.00	1.50	Reeded	5,000,000	15,396,000
Commemorative:							
100 korun	500 Ag, 400 Cu, 50 Ni, 50 Zn	13.00	31.00	2.25	ditto	70,000	265,000
50 korun	ditto	7.00	27.00	1.65	ditto	70,000	90,000
Total						120,721,000	114,701,000

[1] Also reeded.

NOTE: Coinage produced by State Mint, Kremnica. All coins dated year of mintage.

DENMARK

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989[1]	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
20 krone	92% Cu, 6% Al, 2% Ni	9.30	27.00	2.35	Milled[2]	2,800,000	34,400,000
10 krone	do	7.00	23.35	2.30	Plain	38,300,000	12,200,000
5 krone	75% Cu, 25% Ni	9.20	28.50	2.00	Reeded	100,000	46,700,000
1 krone	do	6.80	25.50	1.74	do	15,700,000	.....
50 ore	97% Cu, 2.5% Zn, 0.5% Sn	4.30	21.50	1.57	Plain	92,200,000	63,500,000
25 ore	do	2.80	17.50	1.55	do	100,000	109,100,000
Commemorative:							
200 krone	800 Ag, 200 Cu	31.10	38.00	2.60	Plain	.....	133,000
20 krone	92% Cu, 6% Al, 2% Ni	9.30	27.00	2.35	Milled[2]	.....	1,000,000
Total						149,200,000	267,033,000

[1] Coins variously dated 1989 and 1990.
[2] Interrupted
NOTE: The 5 krone coins contain a 5.5 mm central hole. All coins dated year of mintage except as noted above.

DOMINICAN REPUBLIC

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
1 peso	75% Cu, 25% Ni	20.00	34.00	2.55	Reeded	152,000[1]	30,000,000
50 centavos	Nickel bonded steel	11.25	30.60	1.95	do	8,002,800[2]	1,500,000
25 centavos	do	5.62	24.30	1.85	do	16,002,800[2]	20,000,000
10 centavos	do	2.25	17.90	1.40	do	40,002,800[2]	.....
5 centavos	do	4.50	21.20	1.85	Plain	50,002,800[2]	.....
1 centavo	Zinc plated copper	2.00	19.02	1.30	do	2,815[2]	.....
Commemorative:							
500 peso	999 Au	31.10	40.00	1.85	Reeded	3,000	.....
Do	917 Au	16.96	40.00	n.a	do	.....	1,500,000
Do	999 Platinum	31.10	40.00	n.a	do	30	.....
Do	do	155.53	n.a.	n.a	do	.....	50
100 peso	999 Au	155.53	65.00	n.a	Plain	30	50
Do	999 Ag	311.06	65.00	9.05	do	200	.....
Do	do	155.53	65.00	4.65	do	.....	1,000,000
Do	do	155.53	65.00	4.50	do	6,000	.....
1 peso	999 Au	31.10	34.00	n.a	Reeded	30	10,000,000
Do	999 Ag	31.10	34.00	n.a	do	6,000	50
Total						114,181,305	64,000,150

[1] Figures includes 2,000 proof coins.
[2] Figures includes 2,800 collector sets (five coins each)
NOTE: Coinage produced by the Royal Canadian Mint. All coins dated year of mintage.
n.a. - Not available.

ECUADOR

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
1 sucre	94% Steel, 6% Ni	3.00	20.00	1.50	Serrated	.....	30,000,000
Total							30,000,000

NOTE: Coinage produced by Vereinigte Deutsche Metalwerke, Nickel Technology, A.G., Germany. No coins were produced in 1989.

EGYPT

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
20 piasters	75% Cu, 25% Ni	6.00	27.00	n.a	Serrated	11,490,000	10,025,000
10 piasters	.....do.....	4.50	25.00	n.a	.....do.....	12,412,000	43,302,000
5 piasters	92% Cu, 8% Al	4.90	23.00	n.a	Smooth	49,790,000	65,500,000
2 piasters	.....do.....	3.20	20.00	n.a	.....do.....	500,000	.....
1 piaster	.....do.....	2.00	18.00	n.a	.....do.....	5,000,000	.....
Commemorative:							
5 pounds	875 Au, 100 Cu, 25 Ag	26.00	33.00	n.a	Serrated	1,650	730
Do	720 Ag, 280 Cu	17.50	37.00	n.a	.....do.....	43,000	28,000
1 pound	875 Au, 100 Cu, 25 Ag	8.00	24.00	n.a	.....do.....	3,420	1,852
Total						79,240,070	118,857,582

NOTE: Coinage produced by the Egyptain Mint, Cairo. All coins dated year of mintage.

EL SALVADOR

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
1 colon	Stainless steel	1.35	15.00	1.10	Plain	36,000,000	
Total						36,000,000	

NOTE: Coinage produced by Vereinigte Deutsch Metalwerke, Germany. All coins dated year of mintage. No coins were produced in 1990.

ETHIOPIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
1 cent.....	Aluminum.....	0.57	17.00	n.a.	Plain	30,000,000	
Total.....						30,000,000	

NOTE: All coinage produced by Vereinigte Deutsch Metalwerke, Germany. All coins dated 1969 E.C. No coins were produced in 1990.
n.a. - Not availaole.

FIJI

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
50 cents	75% Cu, 25% Ni	15.55	31.51	2.64	Plain	288,000	400,000
Do	Nickel bonded steel 6%	13.44	31.51	2.64	.....do.....	.....	800,000
20 cents	75% Cu, 25% Ni	11.31	28.52	2.41	Milled	676,000	910,000
Do	Nickel bonded steel 6%	9.60	28.52	2.41	.....do.....	.....	1,500,000
10 cents	75% Cu, 25% Ni	5.66	23.60	1.90	.....do.....	1,500,000	744,000
Do	Nickel bonded steel 6%	4.75	23.60	1.90	.....do.....	.....	2,000,000
5 cents	75% Cu, 25% Ni	2.83	19.41	1.45	.....do.....	2,000,000	2,184,000
Do	Nickel bonded Steel 6%	2.34	19.41	1.45	.....do.....	.....	4,000.000
2 cents	97% Cu, 2.5% Zn, 0.5% Sn	3.89	21.08	1.60	Plain	1,250,000	2,695,000
Do	Copper plated zinc	3.16	21.08	1.60	.....do.....	.....	5,500,000
1 cent	97% Cu, 2.5% Zn. 0.5% Sn	1.94	17.53	1.22	.....do.....	4,000,000	21,000,000
Do	Copper plated zinc	1.58	17.53	1.22	.....do.....	.....	8,500,000
Total						9,714,000	50,233,000

NOTE: All coinage produced by the Royal Australian Mint except the nickel bonded steel 6% and copper plated zinc coins produced by the Royal Canadian Mint. All coinage dated 1987 except the coins produced by the Royal Canadian Mint which were dated 1990.

FINLAND

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
5 markkaa	93% Cu, 5% Al, 2% Ni	8.20	26.30	2.14	Lettered	10,200,000	9,900,000
1 markka	75% Cu, 25% Ni	6.10	24.00	1.77	....do....	37,500,000	50,300,000
50 pennia	93% Cu, 5% Al, 2% Ni	5.50	25.00	1.76	Reeded	10,600,000	5,400,000
Do	75% Cu, 25% Ni	3.30	19.70	1.53	....do....	....	70,500,000
20 pennia	93% Cu, 5% Al, 2% Ni	4.50	22.50	1.80	....do....	40,700,000	9,200,000
10 pennia	97.5% Al, 2.5% Mg	1.00	20.00	1.50	Plain	2,400,000	2,300,000
Do	75% Cu, 25% Ni	1.80	16.30	1.15	....do....	....	338,100,000
5 pennia	....do....	0.80	18.00	1.41	....do....	2,200,000	2,500,000
Commemorative:							
100 markkaa	830 Ag, 170 Cu	24.00	35.00	3.00	Lettered	200,000	250,000
Total						103,800,000	488,450,000

NOTE: Coinage produced by the Mint of Finland. All coins dated year of mintage.

GERMANY

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular Coins:							
5 Deutsche Mark.....	75% Cu. 25% Ni. 100% Ni core.....	10.00	29.00	2.07	Lettered	52,800,000	66,850,000
2 Deutsche Mark.....	.....do.....	7.00	26.75	1.79	.....do.....	56,910,000	169,500,000
1 Deutsche Mark.....	75% Cu. 25% Ni.....	5.50	23.50	1.75	Plain[1]	112,580,000	330,590,000
50 pfennig.....	.....do.....	3.50	20.00	1.58	Smooth	96,670,000	366,760,000
10 pfennig.....	Brass(72-78% Cu). plated on an iron core.....	4.00	21.50	1.70	.....do.....	432,780,000	567,440,000
5 pfennig.....	.....do.....	3.00	18.50	1.70	.....do.....	306,980,000	348,790,000
2 pfennig.....	Cu plated on an iron core.....	2.90	19.25	1.52	.....do.....	192,380,000	242,780,000
1 pfennig.....	.....do.....	2.00	16.50	1.38	.....do.....	364,180,000	568,180,000
Commemorative:							
10 Deutsche Mark.....	.....n.a.....	n.a.	n.a.	n.a.	n.a.	24,960,000	8,010,000
Total.....						1,640,240,000	2,668,900,000

[1] With arabesques.

NOTE: Coinage produced by the German Government Mints. All coins dated year of mintage.

n.a. - Not available.

GHANA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
50 cedi	75% Cu, 25% Ni	7.50	27.50	n.a.	Milled		
20 cedi	Nickel Plated Steel	5.50	24.50	n.a.	Plain		
10 cedi	.....do.....	3.50	21.70	n.a.	.....do.....		
Total							n.a.

NOTE: Coinage produced by Royal Mint U.K. No coins produced in 1989.
n.a. - Not available.

GREECE

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
50 drachmas	92% Cu, 6% Al, 2% Ni	9.00	27.50	2.25	Milled	40,698,432	34,210,947
20 drachmas	do	7.00	24.50	1.80	do	.....	41,772,923
Do	75% Cu, 25% Ni	11.00	29.00	2.30	Lettered	28,511,379	.....
10 drachmas	do	7.50	26.00	1.95	Plain	25,635,966	29,272,348
5 drachmas	do	5.50	22.50	1.85	do	13,057,785	36,182,719
2 drachmas	99.9% Cu, 0.1%.Ni	3.75	21.00	1.48	do	25,258,705	25,420,469
1 drachma	do	2.75	18.00	1.46	do	32,464,029	21,079,636
Total						165,626,296	187,939,042

NOTE: All 1989 coins were dated 1988. All 1990 coins dated year of mintage.

GUATEMALA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
25 centavos	61% Cu, 20% Zn, 19% Ni	8.00	27.00	2.00	Lettered	8,066,000	10,000,000
10 centavos	.....do	3.20	21.00	1.25	Serrated	15,750,000	20,000,000
5 centavos	.....do	1.60	16.00	1.10	.....do.....	25,000,000	20,000,000
1 centavo	70% Cu, 30% Zn	2.50	19.00	1.25	Smooth	60,000,000	76,000,000
Total						108,816,000	126,000,000

NOTE: All coins produced by the Guatemala Mint. All coins dated year of mintage.

GUYANA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
25 cents	Cu 75%, Ni 25%	4.25	22.00	1.52	Milled	6,000,000	.....
10 cents	.....do.....	2.75	18.10	1.47	.....do.....	4,000,000	.....
5 cents	Cu 79%, Zn 20%, Ni 1%	2.50	19.15	1.22	Smooth	3,000,000	3,000,000
1 cent	.....do.....	1.50	16.00	1.17	.....do.....	8,000,000	.....
Total						21,000,000	3,000,000

NOTE: All coins produced by the Royal Mint, U.K. All coins dated year of mintage.

HAITI

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
50 centimes	Zinc, copper, nickel	n.a.	29.00	1.99	Plain	2,000,000	
20 centimes	.....do.....	n.a.	26.20	1.99	.....do.....	2,500,000	
Total						4,500,000	

NOTE: Coinage produced by the Royal Mint, U.K. No coins were produced in 1990.
n.a. - Not available.

HONDURAS

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
50 centavos	75% Cu, 25% Ni	5.67	24.00	1.52	Milled	.....	5,000,000
20 centavos	.....do.....	2.27	18.00	1.04	.....do.....	.....	10,000,000
10 centavos	70% Cu, 30% Ni	6.00	24.00	1.55	Plain	15,000,000	.....
5 centavos	.....do.....	3.20	21.00	1.68	.....do.....	20,000,000	.....
Total						35,000,000	15,000,000

NOTE: Coinage produced by the Royal Canadian Mint, the Royal Mint, U.K., and Vereinigte Deutsche Metalwerke, Germany. All coins dated year of mintage.

HONG KONG

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
5 dollars	75% Cu, 25% Ni	13.50	27.00	3.25	Patterned	30,000,000	15,000,000
2 dollars	.....do.....	8.41	28.00	2.00	Plain	32,000,000	39,000,000
1 dollar	.....do.....	7.10	25.50	1.90	Milled	37,000,000	63,000,000
50 cents	79% Cu, 20% Zn, 1% Ni	4.92	22.50	1.75	.....do.....	.....	27,000,000
20 cents	.....do.....	2.59	19.00	1.40	Plain	30,000,000	39,000,000
10 cents	.....do.....	1.85	17.50	1.06	.....do.....	80,000,000	69,000,000
Total						209,000,000	252,000,000

NOTE: Coinage produced by the Royal Mint, U.K. All coins dated year of mintage.

ICELAND

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
1 krona	Nickel plated steel	4.00	21.50	1.68	Milled		5,180,000
Total							5,180,000

NOTE: All coins produced by the Royal Mint. U.K. All coins produced in 1990 were dated 1991. No coins were produced in 1989.

INDIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
5 rupee	75% Cu. 25% Ni	12.50	31.00	2.00	n.a.	21,774,000	13,930,000
2 rupee	.....do	8.00	28.00	2.00	n.a.	.....	25,072,500
1 rupee	.....do	6.00	26.00	1.80	n.a.	264,010,550	125,360,000
50 paise	.....do	5.00	24.00	1.50	n.a.	81,456,000	21,950,220
Do	Ferretic Stainless Steel 403 modified	3.79	22.00	n.a.	n.a.	76,406,000	38,101,980
25 paise	75% Cu. 25% Ni	2.50	19.00	1.20	n.a.	98,840,000	23,615,840
Do	Ferretic Stainless Steel 403 modified	2.83	19.00	n.a.	n.a.	96,815,000	97,515,000
20 paise	96% Al. 4% Mg	2.20	26.00	2.20	Hexagon	18,812,500	2,000
10 paise	.....do	1.75	23.00	2.20	Scallop	100,915,000	53,480,000
Do	Ferretic Stainless Steel 403 modified	2.00	16.00	n.a.	n.a.	247,710,000	80,060,000
Total						1,006,739,050	479,087,540

NOTE: Coinage produced by the Indian Government Mint except for 8,640,000 50 paise, 51,840,000 25 paise and 166,400,000 10 paise coins dated 1989 which were struck by foreign mints. All coins dated year of mintage.

n.a. - Not available.

INDONESIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
100 rupiah	Copper and Nickel	7.00	28.50	1.50	Serrated	160,375,000	168,000,000
50 rupiah	.....do.....	6.06	24.00	1.50	.....do.....	62,450,000	169,000,000
25 rupiah	.....do.....	3.52	20.00	1.25	.....do.....	30,760,000	61,360,000
Total						253,585,000	398,360,000

NOTE: 100 rupiah coins dated 1978. 50 and 25 rupiah coins dated 1971.

IRELAND

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989[1]	1990[2]
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
1 pound	75% Cu, 25% Ni	10.00	31.10	1.90	Milled[3]	.....	50,200,000
50 pence	.....do.....	13.50	30.00	2.50	Plain[4]	5,000,000	.....
20 pence	79% Cu, 20% Zn, 1% Ni	8.47	27.10	2.00	Milled[5]	11,100,000	4,200,000
5 pence	75% Cu, 25% Ni	5.66	23.60	1.73	Milled	7,500,000	10,500,000
2 pence	97% Cu, 2.5% Zn, 0.5% Sn	7.13	25.91	1.78	Plain	12,500,000	10,200,000
Do	Copper plated mild steel	7.13	25.91	1.78	.....do.....	.....	6,000,000
1 penny	97% Cu, 2.5% Zn, 0.5% Sn	3.56	20.32	1.50	.....do.....	24,400,000	19,800,000
Do	Copper plated mild steel	3.56	20.32	1.50	.....do.....	.....	8,600,000
Total						60,500,000	109,500,000

[1] All coinage dated 1988 except 5 pence which were dated 1986.
[2] Coinage variously dated 1986, 1988 and 1990.
[3] With beading.
[4] Heptagon
[5] Alternating arcs of milled and plain.
NOTE: All coinage produced by Currency Center, Dublin except for 30,000,000 1 pound, 5,000,000 50 pence, and the copper plated 2 pence and 1 penny coins produced by the Royal Mint, U.K.

ISRAEL

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
5 sheqalim	75% Cu. 25% Ni	8.20	24.00	n.a.	12-sided	.....	17,000,000
1 sheqel	.....do.....	4.00	18.00	n.a.	Smooth	12,096,000	1,680,000
1/2 sheqel	92% Cu. 6% Al. 2% Ni	6.50	26.00	n.a.	.....do.....	1,296,000	2,328,000
10 agorot	.....do.....	4.00	22.00	n.a.	.....do.....	1,638,000	4,944,000
5 agorot	.....do.....	3.00	19.50	n.a.	.....do.....	6,192,000	2,640,000
1 agora	.....do.....	2.00	17.00	n.a.	.....do.....	13,392,000	648,000
Total						34,614,000	29,240,000

NOTE: All coins produced by the Jerusalem Mint except 1.080,000 1 sheqel produced in 1990, and the 5 sheqalim coins produced by the Stuttgart Mint, Germany.
n.a. - Not available.

ITALY

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
500 lire	Bimetallic	6.80	25.80	1.90	Serrated	155,000,000	130,000,000
200 lire	92% Cu. 6% Al. 2% Ni	5.00	24.00	1.65	do	42,000,000	64,500,000
100 lire	81.75% Fe. 18.25% Cr	8.00	27.80	2.00	do	34,000,000	.....
Do	do	3.30	18.30	1.80	do	.....	60,000,000
50 lire	do	6.25	24.80	2.00	do	26,500,000	.....
Do	do	2.70	16.55	1.90	Smooth	.....	45,500,000
20 lire	92% Cu. 6% Al. 2% Ni	3.50	21.30	1.50	do	16,000,000	15,500,000
10 lire	96.2% Al. 3.5% Mg. 0.3% Mn	1.50	23.30	1.65	do	16,000,000	14,000,000
5 lire	do	1.00	20.20	1.40	do	2,500,000	2,500,000
2 lire	do	0.80	18.30	1.45	do	60,460	61,700
1 lira	do	0.63	17.20	1.20	do	60,460	61,700
Commemorative:							
500 lire	835 Ag. 165 Cu	11.00	29.00	2.10	Lettered	392,403	379,400
200 lire	do	5.00	24.00	1.65	Serrated	216,500	.....
Total						292,729,823	332,502,800

[1] Central disk 92% Cu. 6% Al. 2% Ni surrounded by a ring of stainless steel.
NOTE: Coinage produced by the Italian Mint. All coins dated year of mintage.

JAMAICA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
1 dollar	70% Cu, 24.5% Zn, 5.5% Ni	9.00	24.00	2.60	Milled[1]	.....	5,000,000
50 cents	75% Cu, 25% Ni	12.48	30.00	2.24	10-sided	5,000,000	.....
25 cents	.....do.....	14.14	32.31	2.24	Milled	10,000,000	.....
20 cents	.....do.....	11.31	28.50	2.30	.....do.....	10,000,000	.....
10 cents	.....do.....	5.66	23.60	1.76	.....do.....	30,240,000	5,000,000
5 cents	.....do.....	2.83	19.40	1.35	.....do.....	20,000,000	5,000,000
1 cent	NS4 Al	1.28	21.08	1.60	12-sided	.....	10,000,000
Total						75,240,000	25,000,000

[1] With incuse lettering.

NOTE: Coinage produced by the Royal Mint, U.K. All coins dated year of mintage.

JAPAN

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
500 yen	75% Cu, 25% Ni	7.20	26.50	1.80	Lettered	208,894,000	159,953,000
100 yen	do	4.80	22.60	1.70	Milled	369,000,000	444,953,000
50 yen[1]	do	4.00	21.00	1.75	do	245,000,000	274,953,000
10 yen	95% Cu, 3-4% Zn, 1-2% Sn	4.50	23.50	1.50	Smooth	741,000,000	754,953,000
5 yen[2]	60-70% Cu, 30-40% Zn	3.75	22.00	1.50	do	1,027,992,000	520,953,000
1 yen	100% Al	1.00	20.00	1.50	do	2,483,070,000	2,768,953,000
Commemorative:							
100,000 yen	Au	30.00	33.00	2.40	Milled	...	2,000,000
5,000 yen	925 Ag, 75 Cu	15.00	30.00	2.60	do	...	20,000,000
500 yen	75% Cu, 25% Ni	13.00	30.00	2.60	do	...	5,000,000
Total						5,074,956,000	4,951,718,000

[1] 50 yen has a central hole 4 mm in diameter.
[2] 5 yen has a central hole 5 mm in diameter.
NOTE: Coinage produced by Japanese Government Mint.

JORDAN

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
100 fils	75% Cu. 25% Ni	12.00	30.00	2.20	Milled	4,000,000	
50 fils	.....do	7.50	26.00	1.90	.....do.....	6,000,000	
10 fils	97% Cu. 2.5% Zn. 0.5% Sn	6.00	25.00	1.80	Plain	8,000,000	
Total						18,000,000	

NOTE: Coinage produced by the Royal Mint. U.K. All coins dated year of mintage. No coins produced in 1990.

KOREA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
500 Won	75% Cu. 25% Ni	7.70	26.50	1.92	Milled	25,000,000	60,000,000
100 Won	.....do.....	5.42	24.00	1.75	.....do.....	250,000,000	185,000,000
50 Won	70% Cu. 18% Zn. 12% Ni	4.16	21.60	1.60	.....do.....	70,000,000	85,000,000
10 Won	65% Cu. 35% Zn	4.06	22.86	1.60	Smooth	310,000,000	395,000,000
5 Won	.....do.....	2.95	20.40	1.39	.....do.....	600,000	600,000
1 Won	100% Al	0.73	17.20	1.39	.....do.....	10,000,000	6,000,000
Total						665,600,000	731,600,000

NOTE: Coinage produced by the Korea Security Printing and Minting Corporation. All coins dated year of mintage.

LIBERIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
1 dollar	75% Cu, 25% Ni	10.65	30.50	n.a.	Milled	90,000	110,000
50 cents	.....do	7.90	27.50	n.a.	.....do	75,000	75,000
25 cents	.....do	5.55	24.50	n.a.	.....do	75,000	25,000
5 cents	Cupro-Nickel	4.15	19.99	n.a.	Plain	18,750	6,250
1 cent	Bronze	2.59	17.91	n.a.	.....do	12,000	13,000
Total						270,750	229,250

NOTE: Coins produced by the Royal Mint, U.K. All 1 and 5 cent coins dated 1977; all others dated 1968.
n.a. - Not available.

LUXEMBOURG

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
50 francs	100% Ni	7.00	22.75	2.30	Reeded	3,200,000	2,000,000
20 francs	999 Au	6.22	21.00	1.35	Plain	50,000	.....
Do	92% Cu, 6% Ni, 2% Al	8.50	25.65	2.50	Scalloped	.....	1,100,000
5 francs	.....do	5.50	24.00	1.75	Plain	2,000,000	4,000,000
1 franc	Steel and Ni	2.75	18.00	1.65	.....do.....	3,000,000	25,000,000
Total						8,250,000	32,100,000

NOTE: Coinage produced by the Royal Mint, Belgium. All coins dated year of mintage.

MADAGASCAR

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
100 francs	75% Ni. 25% Cu clad to a core of pure nickel	12.00	30.50	2.00	Milled	.....	4,950,000
50 francs	.....do.....	9.00	26.50	2.00	.....do.....	.....	7,540,000
20 francs	92% Cu. 6% Al. 2% Ni	6.00	24.50	1.70	Smooth	4,320,000	996,000
10 francs	.....do.....	3.50	21.00	1.70	.....do.....	6,720,000	6,480,000
5 francs	Stainless Steel	5.00	22.00	2.00	.....do.....	7,800,000	12,200,000
2 francs	.....do.....	3.40	19.00	1.88	.....do.....	.....	2,000,000
1 franc	.....do.....	2.40	17.00	1.66	.....do.....	.....	1,500,000
Total						18,840,000	35,666,000

NOTE: 100 and 50 franc coins were produced by the Royal Mint. U.K.; 20 and 10 franc coins produced by the Royal Canadian Mint; and 5, 2 and 1 franc coins were produced by the Administration des Monnaies et Medailles. France. All coins dated year of mintage.

MALAWI

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
50 tambala	Copper. Zinc and Nickel	11.31	30.00	n.a.	Milled	.....	
20 tambala	75% Cu. 25% Ni	11.31	28.50	n.a.	.....do.....	10,000,000	
10 tambala	.....do.....	5.66	23.60	n.a.	.....do.....	11,000,000	
5 tambala	.....do.....	2.83	19.41	n.a.	.....do.....	11,000,000	
2 tambala	Copper plated steel	3.56	20.32	n.a.	Plain	10,550,000	
1 tambala	.....do.....	1.78	17.15	n.a.	.....do.....	10,715,000	
Total						53,265,000	n.a.

NOTE: Coinage produced by the Royal Mint, U.K. All coins dated year of mintage.
n.a. - Not available.

MALAYSIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
1 ringgit	84% Cu, 12% Zn, 4% Sn	9.30	24.50	2.55	Milled	20,409,995	80,101,998
50 sen	75% Cu, 25% Ni	9.33	27.76	2.18	Lettered	6,639,057	26,276,464
20 sen	.....do.....	5.65	23.60	1.75	Milled	28,945,225	56,249,193
10 sen	.....do.....	2.83	19.41	1.37	.....do.....	32,391,768	132,982,376
5 sen	.....do.....	1.41	16.26	1.04	.....do.....	20,484,310	58,909,374
1 sen	Copper plated steel	1.74	17.78	1.27	Plain	28,429,082	102,539,178
Commemorative:							
250 ringgit	900 Au, 60 Ag, 40 Cu	8.64	22.07	1.70	Milled	5,000	.....
30 ringgit	925 Ag, 75 Cu	22.00	32.79	2.50	.....do.....	57,000	.....
25 ringgit	.....do.....	21.70	35.70	2.70	.....do.....	53,000	50,000
15 ringgit	.....do.....	18.80	32.00	2.50	.....do.....	92,500	.....
10 ringgit	.....do.....	13.60	30.50	2.30	.....do.....	20,000	.....
5 ringgit	84% Cu, 12% Zn, 4% Sn	10.40	26.00	2.80	.....do.....	745,500	100,000
Total						138,272,437	457,208,583

NOTE: Coinage produced by Kilang Wang, Malaysia. All coins dated year of mintage.

MALI

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
100 francs	Pure nickel	7.00	26.00	2.00	Milled	.....	500,000
50 francs	75% Cu, 25% Ni	5.00	22.00	1.50	.....do.....	.....	976,000
25 francs	92% Cu, 6% Al, 2% Ni	8.00	27.00	3.00	.....do.....	.....	1,152,000
10 francs	.....do.....	4.00	23.50	1.00	Plain	2,000,000	2,500,000
5 francs	.....do.....	3.00	20.00	1.00	.....do.....	1,500,000	3,000,000
Total						3,500,000	8,128,000

NOTE: Coinage produced by the Administration des Monnaies et Medailles, Paris.

MALTA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in 1989[1]	Coinage in 1990[2]
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
1 lira	100% Ni	13.00	29.82	2.45	Plain	.....	179,966
25 cents	75% Cu. 25% Ni	6.19	24.95	1.82	Beaded	.....	395,784
10 cents	.....do.....	5.01	21.78	1.83	Milled	977,659	599,530
5 cents	.....do.....	3.51	19.78	1.59	.....do.....	1,431,488	1,461,527
2 cents	.....do.....	2.26	17.78	1.43	.....do.....	3,694,753	2,448,584
1 cent	79% Cu. 20% Zn. 1% Ni	2.81	18.51	1.43	Plain	3,458,278	2,804,850
Commemorative:							
100 lira	750 Au. 140 Ag. 110 Cu	17.00	25.00	n.a.	Milled	2,750	.....
5 lira	925 Ag. 75 Cu	28.28	38.61	2.96	.....do.....	93	11,301
Do	.....do.....	20.00	35.20	n.a.	.....do.....	.....	170
2 lira	.....do.....	17.00	30.00	n.a.	.....do.....	57,860	.....
Total						9,622,881	7,901,712

[1] Coins dated variously 1986. 1988 and 1989.
[2] Coins dated variously 1986. 1988 and 1990.
NOTE: Coinage produced by the Malta Mint except for a portion of the 100, 5 and 2 lira produced by the Royal Mint, U.K.
n.a. - Not available.

MEXICO

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
1000 pesos	92% Cu. 6% Al. 2% Ni	14.90	31.00	2.92	Reeded	215,710,000	50,459,000
500 pesos	75% Cu. 25% Ni	12.70	28.50	2.62	.....do.....	40,000,000	.....
100 pesos	92% Cu. 6% Al. 2% Ni	11.80	26.50	3.10	Milled[1]	133,920,000	248,000,000
50 pesos	82% Fe. 18% Cr	7.30	23.50	2.60	Reeded	.....	180,000,000
20 pesos	92% Cu. 6% Al. 2% Ni	5.90	21.00	2.58	.....do.....	287,310,000	126,670,000
10 pesos	82% Fe. 18% Cr	3.80	19.00	2.05	Plain	338,260,000	101,000,000
Bullion:							
50 pesos	900 Au. 100 Cu	41.66	37.00	2.71	Lettered	590,300	247,900
20 pesos	.....do.....	16.66	27.50	2.03	.....do.....	8,000	7,000
10 pesos	.....do.....	8.33	22.50	1.44	.....do.....	.....	10,000
5 pesos	.....do.....	4.16	19.00	1.08	.....do.....	.....	16,000
2 pesos	.....do.....	1.66	13.00	1.04	Reeded	309,000	240,000
Onza Libertad	999 Ag	31.10	36.00	3.52	.....do.....	1,666,071	1,248,000
Numismatic:							
250 pesos	900 Au, 100 Cu	8.64	23.00	1.45	Plain	10,000	.....
100 pesos	720 Ag. 280 Cu	31.10	38.00	3.40	.....do.....	1,300	6,243
Do	925 Ag. 75 Cu	33.62	38.00	3.45	.....do.....	3,500	.....
Total						1,017,707,171	707,904,143

[1] Discontinued mill.

NOTE: Coinage produced by the Mexican Mint.

MOROCCO

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*

NOTE: No coins were produced in 1989 and 1990.

MOZAMBIQUE

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*

NOTE: No coins were produced in 1989 and 1990.

NEPAL

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
50 paisa	97.5% Al. 2.5% Mg	4.50	23.50	1.30	Plain	.....	1,892,468
Do	Nickel bonded steel	4.50	23.50	n.a.	.....do.....	6,388,562	10,000,000[1]
25 paisa	.....do.....	1.80	24.50	1.40	.....do.....	14,502,762	13,336,086
10 paisa	.....do.....	1.30	21.50	1.30	.....do.....	7,029,149	8,829,670
5 paisa	.....do.....	0.80	18.00	1.20	.....do.....	799,911	628,118
Commemorative:							
asarfi	999 Au	5.00	23.50	n.a.	Serrated	1,531	3,733
asarfi	.....do.....	10.00	29.00	n.a.	.....do.....	1,814	.....
asarfi	.....do.....	10.00	27.50	n.a.	.....do.....	.....	2,199
asarfi[2]	.....do.....	11.66	28.50	n.a.	.....do.....	1,000	.....
asarfi[2]	.....do.....	31.10	32.50	n.a.	.....do.....	200	.....
asarfi[2]	.....do.....	15.55	27.00	n.a.	.....do.....	200	.....
asarfi[2]	.....do.....	7.78	21.95	n.a.	.....do.....	300	100
asarfi[2]	.....do.....	3.11	17.95	n.a.	.....do.....	1,500	1,000
1000 rupees	999 Ag	155.50	65.00	n.a.	.....do.....	500	.....
500 rupees	925 Ag	31.10	38.70	n.a.	Milled	5,000	.....
250 rupees	.....do.....	18.00	36.00	n.a.	Plain	4,501	.....
5 rupees	Cupro-Nickel	8.50	29.00	n.a.	.....do.....	.....	77,295
Total						28,736,930	34,770,669

[1] Produced by the Royal Canadian Mint

[2] Produced by the Singapore Mint.

NOTE. Coins produced in 1989 are variously dated 2045, 2046, 1988 and 1989. Coins produced in 1990 are variously dated 2046, 2047 and 1988. Coins produced by the Nepal Rastra Bank, Department of Mint, Kathmandu, Nepal, except as noted above.

n.a. - Not available

NETHERLANDS

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
50 guilders	925 Ag	25.00	38.00	2.45	Lettered[1]	.....	800,000
5 guilders	Aureate Nickel	9.25	23.50	2.75	.....do.....	69,000,000	47,200,000
2.5 guilders	100% Ni	10.00	29.00	2.15	.....do.....	4,000,000	1,000,000
1 guilder	.....do.....	6.00	25.00	1.70	.....do.....	1,000,000	1,000,000
25 cents	.....do.....	3.00	19.00	1.45	Milled	30,400,000	23,000,000
10 cents	.....do.....	1.50	15.00	1.25	.....do.....	5,200,000	13,200,000
5 cents	95% Cu. 4% Sn. 1% Zn	3.50	21.00	1.45	Plain	27,000,000	39,200,000
Total						136,600,000	125,400,000

[1]Also milled

NOTE: All coin dated year of mintage.

NEW ZEALAND

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
2 dollars	92% Cu, 6% Al, 2% Ni	10.00	26.50	2.70	Beaded	.....	30,000,000
1 dollar	.....do.....	8.00	23.00	2.70	Plain[1]	.....	40,000,000
20 cents	75% Cu, 25% Ni	11.31	28.57	2.30	Milled	5,000,000	5,000,000
10 cents	.....do.....	5.65	23.62	1.70	.....do.....	9,000,000	.....
5 cents	.....do.....	2.83	19.43	1.24	.....do.....	36,000,000	.....
Total						50,000,000	75,000,000

[1] Also milled.

NOTE: 1989 coins produced by the Royal Canadian Mint. 1990 coins produced by the Royal Mint, United Kingdom. All coins dated year of mintage.

NICARAGUA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*

NOTE: No coins were produced in 1989 and 1990.

NORWAY

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
10 krone	81% Cu, 10% Zn, 9% Ni	9.00	24.00	2.80	Smooth	4,200,000	3,034,000
1 krone	75% Cu, 25% Ni	7.00	25.00	1.83	do	6,600,000	9,866,000
50 ore	do	4.80	22.00	1.63	do	11,400,000	1,834,000
10 ore	do	1.50	15.00	1.18	do	81,400,000	145,221,000
Total						103,600,000	159,955,000

NOTE: Coinage produced by the Royal Norwegian Mint. All coins dated year of mintage.

OMAN

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces* [1]
Regular coins:							
100 baizas	Cu. Ni	4.25	21.60	n.a.	Milled	.....	3,302
50 baizas	.....do	6.48	24.00	n.a.	.....do.....	4,000,000	3,302
25 baizas	.....do	3.00	18.00	n.a.	.....do.....	7,000,000	3,302
10 baizas	Bronze	4.76	22.50	n.a.	Plain	6,000,000	3,302
5 baizas	.....do	3.11	19.00	n.a.	.....do.....	5,000,000	3,302
Numismatic:							
20 rial	916.7 Au	20.00	30.00	n.a.	Milled	.....	1,302
2 rial	925 Ag	20.00	30.00	n.a.	.....do.....	.....	2,000
Total						22,000,000	19,812

[1] Coins were used in 1302 deluxe sets including the 20 rial gold coin with the 100, 50, 25, 10 and 5 baiza coins and 2000 regular sets including the 2 rial silver coin with the 100, 50, 25, 10 and 5 baiza coins.

NOTE: Coinage produced by the Royal Mint. U.K. All coins dated year of mintage.

n.a. - Not available.

PAKISTAN

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
50 paisa	75% Cu. 25% Ni	4.00	21.00	1.70	Serrated	31,452,000	32,952,000
25 paisa	.....do	2.50	18.00	1.45	.....do.....	73,216,000	70,436,000
10 paisa	Aluminum	1.25	22.00	1.85	Scallop	41,820,000	41,660,000
5 paisa	.....do	1.00	21.00	1.70	Square	45,530,000	38,320,000
Total						192,018,000	183,368,000

NOTE: Coinage produced by the Pakistan Mint. All coins dated year of mintage.

PANAMA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
						—	

NOTE: No coins were produced in 1989 and 1990.

PARAGUAY

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989[1]	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
100 guaranies	Cupro-Nickel	10.46	24.00	3.00	Serrated	.....	35,000,000
50 guaranies	Stainless Steel	5.56	26.00	1.70	Plain	25,000,000	.....
10 guaranies	.....do.....	4.15	22.00	1.50	.....do.....	40,000,000	.....
1 guarani	.....do.....	2.76	18.00	1.50	.....do.....	15,000,000	.....
Total						80,000,000	35,000,000

[1] Coinage dated 1988.

NOTE: Coinage produced by Vereinigte Deutsche Metalwerke, Nickel Technology, AG, West Germany except the 100 guarani coins produced by Thomas de la Rue and Company, Ltd., U.K. All coins dated year of mintage except as noted above.

PHILIPPINES

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989[1]	1990[2]
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
2 pisos	75% Cu. 25% Ni	12.00	31.00	2.10	Plain	54,148,000	63,703,000
1 piso	.....do	9.50	29.00	2.00	Reeded	78,100,000	46,662,000
50 sentimos	.....do	6.05	25.00	1.70	Plain	81,989,000	2,520,000
25 sentimos	65% Cu. 35% Zn	3.85	21.00	1.63	Reeded	40,748,000	101,768,000
10 sentimos	99.2% Al. 0.8% Mg	1.50	19.00	2.28	Plain	20,591,000	162,500,000
5 sentimos	.....do	1.10	17.00	2.05	.....do.....	24,111,000	101,792,000
1 sentimo	.....do	0.70	15.50	1.73	.....do.....	9,644,000	1,010,000
Numismatic:							
200 pisos	925 Ag	25.00	38.00	n.a.	Reeded	.....	20,000
Total						309,331,000	479,975,000

[1] Coins variously dated 1988 and 1989.
[2] Coins variously dated 1989 and 1990.
NOTE: Coinage produced by the Mint and Gold Refinery of the Philippines except the 200 pisos produced by the Royal Mint, U.K.
n.a. - Not available.

PORTUGAL

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989[1]	1990[2]
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
100 escudos	Bimetallic[3]	8.30	25.00	2.29	Serrated	7,233,289	64,766,727
50 escudos	75% Cu. 25% Ni	9.40	31.00	1.61	.....do.....	21,100,008	.....
20 escudos	.....do.....	6.90	26.50	1.59	.....do.....	36,117,917	.....
10 escudos	79% Cu. 20% Zn. 1% Ni	7.40	23.50	2.40	.....do.....	17,000,008	26,500,008
5 escudos	.....do.....	5.30	21.00	2.13	.....do.....	32,022,568	77,977,448
1 escudo	.....do.....	1.70	16.00	1.22	.....do.....	19,557,706	19,008,008
Total						133,031,496	188,252,191

[1] Coins variously dated 1988 and 1989.
[2] Coins variously dated 1989 and 1990.
[3] Central disk 90% Cu. 5% Al and 5% Ni surrounded by a ring 75% Cu and 25% Ni.
NOTE: Coinage produced by the Portuguese Government Mint, Lisbon.

ROMANIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
10 lei	95% Steel Nickel Clad	4.65	23.00	1.60	Grooved[1]		9,500,000
5 lei	99.5% Aluminum	2.70	29.00	1.80	.....do.....		38,000,000
1 leu	95% Steel Nickel Clad	5.00	24.60	1.60	Plain		5,500,000
Total						n.a.	53,000,000

[1] Sinusoidal groove along the lateral edge interrupted by little rhombic pits.

NOTE: 10 lei coins dated 1990, 5 lei coins dated 1978 and 1 leu coins dated 1966.

n.a. - Not available.

SAN MARINO

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
5 scudo	917 Au	15.00	28.00	1.20	Serrated	30,400	6,500
2 scudo	do	6.00	22.00	0.80	do	6,500	6,800
1 scudo	do	3.00	16.00	0.70	do	7,500	7,300
1.000 lire	835 Ag, 165 Cu	14.60	31.40	2.40	Lettered	70,400	94,800
500 lire	do	11.00	29.00	2.10	do	38,400	58,800
Do	Bimetallic[1]	6.80	25.80	1.90	Serrated	3,112,848	3,711,063
200 lire	92% Cu, 6% Al, 2% Ni	5.00	24.00	1.65	do	1,005,000	.....
100 lire	81.75% Fe, 18.25% Cr	8.00	27.80	2.00	do	5,000	.....
Do	do	3.30	18.30	1.80	do	.....	1,050,000
50 lire	do	6.25	24.80	2.00	do	55,000	.....
Do	do	2.70	16.55	1.90	Smooth	.....	16,000
20 lire	92% Cu, 6% Al, 2% Ni	3.50	21.30	1.50	do	5,000	60,000
10 lire	96.2% Al, 3.5% Mg, 0.3% Mn	1.50	23.30	1.65	do	5,000	.....
5 lire	do	1.00	20.20	1.40	do	5,000	.....
2 lire	do	0.80	18.30	1.45	do	5,000	.....
1 lira	do	0.63	17.20	1.20	do	5,000	.....
Total						4,356,048	5,011,263

[1] Central disk 92% Cu, 6% Al, 2% Ni surrounded by a ring of stainless steel.

NOTE: Coinage produced by the Italian Mint. All coins dated year of mintage.

SAUDI ARABIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*

NOTE: No coins were produced in 1989 and 1990.

SINGAPORE

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
1 dollar	92% Cu, 6% Al, 2% Ni	6.30	22.40	2.40	Milled	47,880,000	52,314,000
50 cents	75% Cu, 25% Ni	7.29	24.66	2.06	do	20,046,000	19,740,000
20 cents	do	4.50	21.36	1.72	do	50,520,000	53,052,500
10 cents	do	2.60	18.50	1.38	do	112,835,000	73,075,000
5 cents	92% Cu, 6% Al, 2% Ni	1.56	16.75	1.22	do	60,020,000	51,040,000
1 cent	97.25% Zn, 2.75% Cu	1.24	15.90	1.10	Plain	.....	20,080,000
Numismatic:							
500 dollars	916 Au, 84 Ag	16.97	28.50	1.95	Milled	5,000	5,000
Do	Platinum	31.10	32.10	2.50	do	.....	2,000
250 dollars	999.9 Au	31.10	32.12	2.52	do	.....	6,000
100 dollars	do	31.10	32.12	2.50	do	.....	7,000
50 dollars	999.9 Au	15.55	27.00	2.00	do	.....	7,000
Do	916 Au, 84 Ag	10.00	25.00	1.55	do	1,000	.....
25 dollars	999.9 Au	7.78	21.96	1.55	do	.....	7,000
10 dollars	do	3.11	17.95	1.10	do	.....	7,000
Do	Nickel	28.00	40.70	3.05	do	330,000	300,000
Do	925 Ag, 75 Ni	31.10	40.70	3.05	do	30,000	80,000
5 dollars	999.9 Au	1.55	13.92	0.90	do	.....	10,000
Do	925 Ag, 75 Cu	20.00	38.70	2.45	do	35,000	.....
Do	75% Cu, 25% Ni	20.00	38.70	2.30	do	60,000	.....
Do	92% Cu, 6% Al, 2% Ni	15.33	33.32	2.55	do[1]	.....	1,000,000
1 dollar	925 Ag, 75 Cu	8.05	22.40	2.40	do[2]	15,000	15,000
Do	92% Cu, 6% Al, 2% Ni	6.30	22.40	2.40	do	100,000	100,000
50 cents	925 Ag, 75 Cu	8.56	24.66	2.06	do[2]	15,000	15,000
Do	75% Cu, 25% Ni	7.29	24.66	2.06	do	100,000	100,000
20 cents	925 Ag, 75 Cu	5.24	21.36	1.72	do	15,000	15,000
Do	75% Cu, 25% Ni	4.50	21.36	1.72	do	100,000	100,000
10 cents	925 Ag, 75 Cu	3.05	18.50	1.38	do	15,000	15,000
Do	75% Cu, 25% Ni	2.60	18.50	1.38	do	100,000	100,000
5 cents	925 Ag, 75 Cu	2.00	16.75	1.22	do	15,000	15,000

SINGAPORE (continued)

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
5 cents	92% Cu. 6% Al. 2% Ni	1.56	16.75	1.22	Milled	100,000	100,000
1 cent	925 Ag. 75 Cu	1.81	15.90	1.10	Plain	15,000	15,000
Do	95% Cu. 4% Zn. 1% Sn	1.53	15.90	1.10	.....do.....	100,000	100,000
Total						292,452,000	271,422,500

[1] With words Republic of Singapore and lion symbol.
[2] With words Republic of Singapore. lion symbol and "25 years."
NOTE: Coinage produced by the Singapore Mint Pte Ltd.

SIERRA LEONE

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*

NOTE: No coins were produced in 1989 and 1990.

SOUTH AFRICA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989[1]	1990[2]
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
2 rands	Core: 95% Cu, 4.5% Zn,0.5% Sn with layer 40micron Ni	5.50	23.00	1.70	Serrated	51,805,789	69,884,469
1 rand	.....do.....	4.00	20.00	1.80	.....do.....	.....	22,469
Do	100% Ni	12.00	31.00	2.22	.....do.....	13,869,221	25,377,514
50 cents	.....do.....	9.50	27.85	2.22	Smooth	17,269,121	29,442,400
Do	Core: FE with layer 40 micron of 85% Cu, 15% Sn	5.00	22.00	2.00	Serrated	.....	22,469
20 cents	100% Ni	6.00	24.21	1.87	Smooth	61,182,721	100,128,000
Do	Core: FE with layer 40 micron of 85% Cu, 15% Sn	3.50	19.00	1.80	Serrated	.....	22,469
10 cents	100% Ni	4.00	20.70	1.71	Smooth	62,206,721	11,375,000
Do	Core: FE with layer 40 micron of 85% Cu, 15% Sn	2.00	16.00	1.60	Serrated	.....	6,254,469
5 cents	100 Ni	2.50	17.35	1.55	Smooth	9,122,261	.....
Do	Core: FE with layer 40 micron of 99% Cu, 1% Sn	4.50	21.00	1.90	Serrated	.....	204,165,519
2 cents	95% Cu, 4.5% Zn, 0.5% Sn	4.00	22.45	1.64	.....do.....	212,826,721	229,104,000
Do	Core: FE with layer 40 micron of 99% Cu, 1% Sn	3.00	18.00	1.80	Smooth	.....	22,469
1 cent	95% Cu, 4.5% Zn, 0.5% Sn	3.00	19.05	1.59	Serrated	329,614,721	28,318,000
Do	Core: FE with layer 40 micron of 99% Cu, 1% Sn	1.50	15.00	1.30	Smooth	.....	141,170,469
Total						757,897,276	845,309,716

[1] Coins variously dated 1988 and 1989.
[2] Coins variously dated 1989 and 1990.
NOTE: Coinage produced by the South African Mint.

SPAIN

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
500 pesetas	88.4% Cu, 5% Al, 5% Ni,1% Fe, 0.6% Mn	12.00	28.00	2.80	Lettered[1]	100,000,000	32,000,000
200 pesetas	75% Cu, 25% Ni	8.50	22.00	2.85	Milled[2]	8,000,000	.....
Do	....do....	10.50	25.50	2.60	....do....	.....	8,000,000
100 pesetas	88.4% Cu, 5% Al, 5% Ni,1% Fe, 0.6% Mn	9.25	24.50	2.90	Lettered	81,000,000	26,000,000
50 pesetas	75% Cu, 25% Ni	5.60	20.50	2.40	Smooth[3]	.....	22,000,000
25 pesetas	88.4% Cu, 5% Al, 5% Ni,1% Fe, 0.6% Mn	4.25	19.50	2.15	....do....	.....	60,000,000
5 pesetas	75% Cu, 25% Ni	5.75	23.00	1.85	Milled	58,000,000	.....
Do	88.4% Cu, 5% Al, 5% Ni,1% Fe, 0.6% Mn	3.00	17.50	1.80	Smooth	42,000,000	193,000,000
1 peseta	96.5% Al, 3.5% Mg	1.20	21.00	1.55	....do....	186,000,000	.....
Do	....do....	0.55	14.00	1.55	....do....	13,000,000	198,000,000
Numismatic:							
100 Ecu	900 Au, 100 Ag	34.55	40.00	1.85	Milled	8,700	1,400
50 Ecu	....do....	17.27	28.00	1.95	....do....	13,000	1,400
10 Ecu	....do....	3.45	16.00	1.20	Smooth	26,500	.....
5 Ecu	925 Ag, 75 Cu	33.62	42.00	2.78	Milled	216,000	18 000
1 Ecu	....do....	6.72	24.00	1.65	....do....	150,000	14,000
Total						488,414,200	539,034,800

[1] Also milled
[2] Also smooth.
[3] With seven notches.
NOTE. All coinage produced by the Spanish Government Mint. Coins variously dated 1989 and 1990.

SRI LANKA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989[1]	1990[2]
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
25 cents	Cupro-nickel	3.24	18.03	1.80	Milled	.....	28,300,000
10 cents	Aluminum	1.30	23.11	1.53	Smooth[3]	40,000,000	.....
5 cents	.....do	1.00	18.24	1.60	.....do.....[4]	40,000,000	2,400
1 cent	.....do	7.00	16.00	1.56	.....do.....	.....	6,000,000
Commemorative:							
5 rupees	Nickel Brass	9.50	23.50	2.95	Milled[5]	18,300,000	11,400,000
2 rupees	Cupro-nickel	8.25	28.50	1.75	.....do.....	.....	11,100,000
Total						98,300,000	56,802,400

[1] Coins variously dated 1986. 1988 and 1989.
[2] Coins variously dated 1984. 1986. 1988 and 1989.
[3] Coin measures 23.11 mm across scallops; 20.96 mm inside scallops.
[4] Coin measures 21.46 mm across corners: 18.24 mm across flats.
[5] Also lettered.
NOTE: All coins produced by the Royal Mint. U.K.

SUDAN, REPUBLIC OF THE

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
1 pound	70% Cu. 24% Zn. 6% Ni	14.00	32.00	2.00	Plain	630,000	.....
Do	Nickel bonded steel	7.50	26.00	1.80	.....do.....	.....	12,750,000
50 piasters	70% Cu. 24% Zn. 6% Ni	12.00	30.00	2.20	Hexagon	1,786,500	.....
Do	Nickel bonded steel	5.00	24.00	1.70	Plain	.....	665,000
25 piasters	70% Cu. 24% Zn. 6% Ni	10.00	30.00	2.10	Square	3,964,000	.....
20 piasters	.....do.....	8.00	27.00	2.00	Plain	145,000	.....
10 piasters	.....do.....	6.00	25.00	1.50	.....do.....	170,000	.....
5 piasters	70% Cu. 28% Zn. 2% Ni	4.00	21.00	1.30	.....do.....	602,000	.....
Total						7,297,500	13,415,000

NOTE: Coinage produced by the Sudan Mint Company. Ltd., Kartoum. 1989 coins are dated 1987; 1990 coins dated 1409/1989.

SWAZILAND

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
20 cent	Cupro-Nickel	5.55	25.20	n.a.	Plain	.....	1,000,000
10 cent	.....do.....	3.63	22.00	n.a.	.....do.....	.....	3,000,000
5 cent	.....do.....	2.11	18.50	n.a.	.....do.....	1,000,000	2,688,000
1 cent	Copper plated steel	1.75	17.00	n.a.	.....do.....	.....	11,700,000
Total						1,000,000	18,388,000

NOTE: All coins dated 1986.
n.a. - Not available.

SWEDEN

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989[1]	1990[2]
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
1000 kronor	900 Au, 50 Ag, 50 Cu	5.80	21.00	1.10	Plain	20,000	15,000
200 kronor	925 Ag, 75 Cu	27.00	36.00	2.30	.....do.....	80,000	50,000
10 kronor	89% Cu, 5% Al, 5% Zn, 1% Sn	6.60	20.50	2.90	Milled[3]	.....	100,000
5 kronor	75% Cu, 25% Ni (Outer),100% Ni (Core)	9.50	28.50	2.00	Plain	2,428,745	10,069,700
1 krona	75% Cu, 25% Ni	7.00	25.00	1.88	Reeded	50,068,745	55,069,700
50 ore	.....do.....	4.50	22.00	1.61	Plain	628,745	23,109,700
10 ore	.....do.....	1.44	15.00	1.14	.....do.....	220,068,745	200,246,542
Total						273,294,980	288,660,642

[1] Coins variously dated 1988 and 1989.
[2] Coins variously dated 1989, 1990 and 1991.
[3] Interrupted
NOTE: Coinage produced by the Swedish Mint, Eskilstuna.

SWITZERLAND

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
5 francs[1]	75% Cu. 25% Ni	13.20	31.00	2.35	Lettered	6,370,000	2,218,000
2 francs	do	8.80	27.00	2.15	Reeded	8,031,000	5,045,000
1 franc	do	4.40	23.00	1.55	do	15,031,000	2,032,000
50 centimes	do	2.20	18.00	1.25	do	10,031,000	20,032,000
20 centimes	do	4.00	21.00	1.65	Smooth	20,031,000	6,534,000
10 centimes	do	3.00	19.00	1.45	do	41,031,000	40,032,000
5 centimes	92% Cu. 6% Al. 2% Ni	1.80	17.00	1.25	do	45,031,000	16,042,000
1 centime	95% Cu. 4% Sn. 1% Zn	1.50	16.00	1.10	do	2,031,000	1,032,000
Total						147,587,000	92,967,000

[1] 5 Franc figures include 1.339.000 commemorative coins for 1989 and 1,169,000 commemorative coins for 1990.

NOTE: Coinage produced by the Swiss Federal Mint. Berne. All coins dated year of mintage.

SYRIAN ARAB REPUBLIC

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*

NOTE: No coins were produced in 1989 and 1990.

THAILAND

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
10 baht	Bimetal: Disc-92% Cu,6% Al, 2% Ni, Ring-75% Cu, 25% Ni	8.50	24.00	n.a.	n.a.	100,000,000[1]	.....
5 baht	75% Cu, 25% Ni	7.50	24.00	n.a.	Milled	86,340,000	38,000,000
1 baht	.....do.....	3.40	20.00	n.a.	.....do.....	466,690,000	409,920,000
50 satangs	92% Cu, 6% Al, 2% Ni	2.40	18.00	n.a.	.....do.....	57,970,000	92,960,000
25 satangs	.....do.....	1.90	16.00	n.a.	.....do.....	58,940,000	81,380,000
10 satangs	97.5% Al, 2.5% Mg	0.80	17.50	n.a.	Plain	80,000	100,000
5 satangs	.....do.....	0.60	16.00	n.a.	.....do.....	460,000	370,000
1 satang	.....do.....	0.50	15.00	n.a.	.....do.....	110,000	190,000
Commemorative:							
6000 baht	900 Au, 30 Ag, 70 Cu	15.00	27.00	n.a.	Milled	435	.....
3000 baht	.....do.....	7.50	21.00	n.a.	.....do.....	108	.....
1500 baht	.....do.....	3.75	17.00	n.a.	.....do.....	483	.....
600 baht	925 Ag. 75 Cu	30.00	37.00	n.a.	.....do.....	62	.....
Do	.....do.....	22.00	35.00	n.a.	.....do.....	10,392	22,500
300 baht	.....do.....	15.00	31.00	n.a.	.....do.....	1,173	.....
150 baht	.....do.....	7.50	27.00	n.a.	.....do.....	683	.....
10 baht	75% Cu, 25% Ni	15.00	32.00	n.a.	.....do.....	13,021	1,445,989
2 baht	.....do.....	7.30	22.00	n.a.	.....do.....	3,000,011	4,000,000
Total						773,616,368	628,388,489

[1] Produced by the Italian Mint.

n.a. - Not available.

TRINIDAD AND TOBAGO

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
10 cents	Cupro-Nickel	1.41	16.28	1.02	Milled	.....	32,000,000
5 cents	Bronze	3.24	21.16	1.35	Plain	.....	15,000,000
1 cent	.....do.....	1.94	17.78	1.14	.....do.....	20,000,000	30,000,000
Total						20,000,000	77,000,000

NOTE: All coins produced by the Royal Mint, U.K. All coins dated year of mintage.

TURKEY

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
1000 lira	69.5% Cu. 18% Zn. 12% Ni. 0.5% Mn	8.10	25.50	2.10	Reeded	.....	136,980,000
500 lira	70% Cu. 30% Zn	6.10	23.75	2.02	.....do.....	131,164,797	100,114,000
100 lira	.....do.....	4.10	20.75	1.70	.....do.....	233,730,288	152,230,000
50 lira	.....do.....	3.30	18.75	1.67	.....do.....	25,462,700	500,000
Total						390,357,785	389,824,000

NOTE: All coins produced by the Turkish State Mint. All coins dated year of mintage.

UNITED KINGDOM

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:							
2 pounds	.....n.a.....	n.a.	n.a.	n.a.	n.a.	4,423,000	350,000
1 pound	70% Cu, 24.5% Zn, 5.5% Ni	9.50	22.50	3.10	Lettered	.....	70,741,000
20 pence	84% Cu, 16% Ni	5.00	21.40	1.75	.....do.....	98,397,000	110,421,000
5 pence	75% Cu, 25% Ni	5.66	23.60	1.73	Milled	154,075,000	101,505,000
Do	.....n.a.....	3.25	18.00	n.a.	n.a.	322,599,000	849,118,000
2 pence	97% Cu, 2.5% Zn, 0.5% Sn	7.13	25.91	1.80	Plain	404,435,000	298,514,000
1 penny	.....do.....	3.56	20.32	1.52	.....do.....	737,449,000	674,637,000
Numismatic:							
5 pounds	916.7 Au, 83.3 Cu	39.94	36.02	2.54	Milled	4,000	3,492
2 pounds	.....do.....	15.98	28.40	n.a.	.....do.....	16,750	7,000
Do	925 Ag, 75 Cu	15.98	28.40	2.68	.....do.....	50,000	.....
Do	.....n.a.....	31.96	28.40	n.a.	.....do.....	20,000	.....
Do	70% Cu, 24.5% Zn, 5.5% Ni	15.98	28.40	2.98	Lettered	682,535	261,375
1 pound	916.7 Au, 83.3 Cu	7.99	22.05	1.49	Milled	27,500	8,750
Do	925 Ag, 75 Cu	9.50	22.50	2.35	Lettered	.....	25,000
Do	.....do.....	19.00	22.50	n.a.	n.a.	10,000	.....
Do	70% Cu, 24.5% Zn, 5.5% Ni	9.50	22.50	3.10	.....do.....	199,000	188,692
1/2 pound	916.7 Au, 83.3 Cu	3.99	19.30	1.06	Milled	24,000	8,500
50 pence	75% Cu, 25% Ni	13.50	30.00	2.50	Plain	199,000	182,023
20 pence	84% Cu, 16% Ni	5.00	21.40	1.75	.....do.....	199,000	182,023
10 pence	.....n.a.....	n.a.	n.a.	n.a.	n.a.	199,000	182,023
5 piedfort	925 Ag, 75 Cu	6.50	18.00	n.a.	n.a.	.....	20,000
5 pence	75% Cu, 25% Ni	5.66	23.60	1.73	Milled	199,000	182,023
2 pence	97% Cu, 2.5% Zn, 0.5% Sn	7.13	25.91	1.80	Plain	199,000	182,023
1 penny	.....do.....	3.56	20.32	1.52	.....do.....	199,000	182,023
Maundy Money:							
4 pence	925 Ag, 75 Cu	1.89	17.63	0.98	.....do.....	1,414	1,554
3 pence	.....do.....	1.41	16.26	0.90	.....do.....	1,540	1,426
2 pence	.....do.....	0.94	13.44	0.89	.....do.....	1,414	1,426
1 penny	.....do.....	0.47	11.15	0.73	.....do.....	1,414	1,426

UNITED KINGDOM (continued)

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Bullion Coins:							
100 pounds	916.7 Au, 83.3 Cu	34.05	32.69	2.76	Milled	3,000	1,500
50 pounds	.....do.....	17.03	27.00	2.07	.....do.....	2,500	1,250
25 pounds	.....do.....	8.51	22.00	1.65	.....do.....	3,500	1,250
10 pounds	.....do.....	3.41	16.50	1.15	.....do.....	5,500	2,500
Total.....						1,724,115,602	2,106,913,279

NOTE: Coinage produced by the Royal Mint,UK.
n.a. - Not available

UNITED STATES

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in 1989[1]	Coinage in 1990[2]
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
Regular coins:	Three layer composition:						
50 cents	75% Cu, 25% Ni (Outer),100% Cu (Core)	11.34	30.61	2.18	Reeded	54,767,634	49,261,861
25 cents	do	5.67	24.26	1.75	do	1,416,827,276	1,548,317,800
10 cents	do	2.27	17.91	1.35	do	2,202,161,015	1,881,223,443
5 cents	75% Cu, 25% Ni	5.00	21.21	1.98	Smooth	1,476,879,892	1,332,462,122
1 cent	97.5% Zn, 2.5% Cu	2.50	19.05	1.57	do	12,614,228,129	11,781,547,172
Commemorative:							
5 dollars	900 Au, 60 Ag, 40 Cu	8.36	21.59	1.42	Reeded	215,560	6,455
1 dollar	900 Ag, 100 Cu	26.73	38.10	2.79	do	871,547	1,401,623
50 cents	Three layer composition:.						
	75% Cu, 25% Ni (outer), 100% Cu (Core)	11.34	30.61	2.18	do	859,808	71,842
Bullion coins:							
50 dollars	917 Au, 30 Ag, 53 Cu	33.93	32.70	2.83	do	480,620	467,080
25 dollars	do	16.97	27.00	2.15	do	106,853	84,497
10 dollars	do	8.48	22.00	1.78	do	130,220	117,526
5 dollars	do	3.39	16.50	1.28	do	359,768	321,161
1 dollar	999 Ag	31.10	40.60	2.94	do	6,781,350	7,943,133
Total						17,774,669,672	16,603,225,715

[1] Regular coin figures include sales of 3,008,015 5-coin proof sets, 215,945 prestige sets and 2,000,729 10-coin uncirculated sets. Commemorative coin figures reflect sales for the U.S. Olympic and Bicentennial of Congress Coin Programs through December 1989. Bullion coin figures reflect sales through December 1989 and include 54,620 gold proof 50 dollar, 44,853 proof 25 dollar, 54,220 gold proof 10 dollar, 84,768 gold proof 5 dollar and 615,350 silver proof one dollar coins.

[2] Regular coin figures include sales of 2,781,615 5-coin proof sets, 512,950 prestige sets and 1,796,527 10-coin uncirculated sets. Commemorative coin figures reflect sales for the Bicentennial of Congress and Eisenhower Coin Programs through December 1990. Bullion coin figures reflect sales through December 1990 and include 62,080 gold proof 50 dollar, 51,497 gold proof 25 dollar, 62,526 gold proof 10 dollar, 99,161 gold proof 5 dollar and 696,133 silver proof one dollar coins.

NOTE Coinage produced by the United States Mint facilities.

URUGUAY

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
500 peso	70% Cu. 30% Ni	11.78	29.00	n.a.	Milled	22,000,000	
200 peso	70% Cu, 20% Ni. 10% Zn	10.00	27.00	n.a.	.....do.....	15,000,000	
100 peso	Stainless Steel	7.56	25.00	n.a.	.....do.....	35,000,000	
50 peso	.....do.....	4.80	23.00	n.a.	.....do.....	42,000,000	
10 peso	.....do.....	2.94	18.00	n.a.	.....do.....	75,000,000	
5 peso	.....do.....	1.36	15.00	n.a.	.....do.....	65,000,000	
1 peso	.....do.....	0.87	12.00	n.a.	.....do.....	500,000	
Total						254,500,000	

NOTE: Coinage produced by the Administration des Monnais et Medailles, Paris. All coins dated year of mintage. No coins were produced for 1990.
n.a. - Not available.

VATICAN CITY

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
1.000 lire	835 Ag, 165 Cu	14.60	31.40	2.40	Lettered	60,000	48,000
500 lire	Bimetallic	6.80	25.80	1.90	Serrated	400,000	380,000
200 lire	92% Cu, 6% Al, 2% Ni	5.00	24.00	1.65	.....do.....	764,000	378,000
100 lire	81.75% Fe, 18.25% Cr	8.00	27.80	2.00	.....do.....	1,000,000	500,000
50 lire	.....do.....	6.25	24.80	2.00	.....do.....	400,000	270,000
20 lire	92% Cu, 6% Al, 2% Ni	3.50	21.30	1.50	Smooth	300,000	121,000
10 lire	96.2% Al, 3.5% Mg, 0.3% Mn	1.50	23.30	1.65	.....do.....	120,000	48,000
Total						3,044,000	1,745,000

NOTE: Coinage produced by the Italian Mint. All coins dated year of mintage.

VENEZUELA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
5 bolivar	Steel, Nickel	13.40	31.00	n.a.	Milled		200,000,000
2 bolivar	.....do.....	7.50	27.00	n.a.	.....do.....		400,000,000
1 bolivar	.....do.....	4.25	23.00	n.a.	.....do.....		600,000,000
50 centimos	.....do.....	3.10	20.00	n.a.	.....do.....		300,000,000
25 centimos	.....do.....	1.50	17.00	n.a.	.....do.....		400,000,000
Total						n.a.	1,900,000,000

NOTE: All coins dated year of mintage.
n.a. - Not available

YUGOSLAVIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989[1]	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
100 dinara	75% Cu, 21% Zn, 4% Ni	5.40	24.00	n.a.	Plain		
50 dinara	do	3.90	21.00	n.a.	do		
20 dinara	do	3.20	19.00	n.a.	do		
10 dinara	do	2.50	17.00	n.a.	do		
5 dinara	70% Cu, 18% Zn, 12% Ni	8.63	28.00	n.a.	do		
2 dinara	do	6.98	26.00	n.a.	do		
1 dinar	do	5.95	24.00	n.a.	do		
50 para	85% Cu, 15% Zn	4.68	22.00	n.a.	do		
20 para	do	3.87	20.00	n.a.	do		
10 para	do	3.14	18.00	n.a.	do		
Total						n.a.	n.a.

[1] Coinage dated 1988.

NOTE: Coinage produced by the Yugoslavian Government Mint, Belgrade. All coins dated year of mintage, except as noted above.

n.a - Not available.

ZAMBIA

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
20 ngwee	60% Cu. 20% Ni. 20% Zn	11.31	1.12	0.09	Milled		3,000,000
10 ngwee	.....do.....	5.66	0.93	0.07	.....do.....		4,000,000
5 ngwee	.....do.....	2.83	0.76	0.06	.....do.....		6,000,000
Total						n.a.	13,000,000

NOTE: Coins dated 1987 and 1988.
n.a. - Not available.

TAIWAN

Denomination	Metallic composition	Gross weight	Diameter	Thickness	Edge	Coinage in	
						1989	1990
		Grams	*mm*	*mm*		*Pieces*	*Pieces*
10 dollar	75% Cu, 25% Ni	7.50	26.00	1.88	Milled	180,000,000	250,000,000
5 dollar	do	4.40	22.00	1.55	do	300,000,000	50,000,000
1/2 dollar	97% Cu, 2.5% Zn, 0.5% Sn	3.00	18.00	1.50	Smooth	.....	30,000,000
Total						480,000,000	330,000,000

NOTE: Coinage produced by the Central Mint of China. All coins dated year of mintage.

LIBRARY
OF
WASHINGTON
UNIVERSITY
ST LOUIS - MO.